

Products	Average Particle Size [µm]	Polymer	Effective Density [g/cm³]	Solids content [%]	Solvent resistance
FN-80SDE	20 - 40	Acrylnitril-Copolymer	0.020 - 0.030	≥ 97	••
F-65DE	40 - 60	Acrylnitril-Copolymer	0.025 - 0.035	≥ 97	••
F-80DE	90 - 130	Acrylnitril-Copolymer	0.015 - 0.025	≥ 97	•••
FN-78DE	100 - 200	Acrylnitril-Copolymer	0.010 - 0.020	≥ 97	•••

Solvent resistance: low: • medium: •• well suited: •••